

BC-GARD SF HCR

A TWO COMPONENT HIGH CHEMICALS NOVOLAC EPOXY COATING

DESCRIPTION:

BC-GARD SF HCR is a high performance developed specifically as high chemicals and an abrasion resistant for areas with light or high traffic; two component high chemicals solvent-free colored novolac epoxy coating. It makes for industrial floors dust free, joint less, glossy finishing and available in a wide range of attractive colors.

PRODUCT FEATURE:

Area of use are light duty industrial for dry process where the floor is subjected to pallet tuck, trolley and fork lift traffic areas, car park deck, include laboratories, electronic and clean rooms, automotive assembly, aircraft hangar, garages, pharmaceutical, printing pulp paper, mills, refineries and other industrial plants sectors where chemical

RCORD SF HAR RCORD SF HAR RCORD SF HAR RCORD SF HAR SUBSTRATE



BENEFITS:

- Seamless, monolithic application.
- Solvent Less, Low Odor and V.O.C
- ➤ Hygienic, easy to clean.
- ➢ High chemical resistance to wide range of chemicals.
- Abrasion resistant, against medium traffic and trolley movement.
- ➤ Hard wearing floors finish
- ➢ Wide range of colours
- Complied with BC6920 requirement

COLORS:

RAL K5 Classic Color Chart

FINISHING:

cure

► Gloss

TECHNICAL DATA

Density (28°C) g/ml ² (mixed)			1.40±0.05g/ml		
Adhesive strength			>2.0N/mm ²		
			(Concrete failure)		
Tensile strength			25N/mm ²		
Compressive strength (28 days)			55N/mm ²		
Flexural strength			35N/mm ²		
Shore D hardness			75 ~ 82		
Temperature Resistance			up to 100°C		
Water Permeability			Nil-Karsten test		
			(impermeable)		
ASTM D 4060 -10 Taber Abraser			37mg		
Wear Index in mg/100					
revolutions/1kg					
BS 6920 : Part 1:2000			< 2.39 or Less		
Dissolved Oxygen difference					
(MDOD),mg/L					
Mixing Ratio by Weight			Part A : Part B		
			4 : 1		
Packaging			5kg & 10kg		
Pot life (working time)(28°C)			30min		
Shelf life & storage 12months					
(unopened and in good conditions					
temperature 10°C to 30°C)					
Material consumption(mixed) 0.17m ² /kg@mm ²					
Curing time:					
	15°C	25°C	32°C		
Human traffic	24hrs	20hrs	18hrs		
Light traffic	36hrs	30hrs	24hrs		
Fully chemicals	10days	7days	7days		



BC-GARD SF HCR

A TWO COMPONENT HIGH CHEMICALS NOVOLAC EPOXY COATING

SUBSTRATE REQUIREMENT & PREPARATION:

Substrate concrete or screed should be a minimum of compressive strength 25N/mm² and adhesive pull-off strength of minimum 1.5N/mm². The substrate should be clean and free from laitance, oil, dust, loose constituents, paint residues, chemicals, algae and other contamination should be removed. The substrate should be dry and free from ground water pressure. If substrate moisture exceeded 4%, apply BC-GARD EM epoxy mortar (compressive strength 60N/mm²) 4-5mm thick or Apply BC-Cem MB 2-3mm thick as a moisture barrier. The substrate must be prepared by vacuum shot blasting, rough contaminations to remove by grinding. Cracks and hollows should be properly remedied. Prepare grooves 3mm wide x 3mm deep at all edges, bay joints columns, doorways and drains for anchoring purpose.

MIXING :

Stir Part A mix for 30 seconds by using a suitable electrical stirrer (with 750 watt High power mixer), than add all of Parts B (Hardener) and mix both liquid parts thoroughly for 2 minute until it fully achieved a homogeneous.

APPLICATION :

- Apply BC-Prime SF @ 0.2kg/m² as a primer for sealing well the substrate porosity.
- Usually within 8-14hours; BC-Prime SF cured, Then only allow to do layering BC-GARD SF HCR. Topping onto the BC- Prime SF Primer.
- Apply BC-GAR SF HCR within the pot life (working time), can be applied by brush or roller.

TEMPERATURE CONDITIONS OF APPLICATIONS:

- Do not apply when the relative humidity exceeds 90% on when the surface to be coated is less than 5% above the dew point.
- Do not apply temperatures below 5°C and temperatures above 40°C

Maintenance and care after cure :

We recommend basic cleaning and maintenance will prolong the life of epoxy floors, clean regularly using a single or double headed rotary scrubber drier in conjunction with alkaline detergent.

Further Information :

Warning and precautions information relating to the safe handling of this product should be found in Material Safety Data Sheet. To be advise to put on suitable clothing and eye-ware for protection purpose. The application area/site must be in good ventilation otherwise advisable to use a portable exhaust fan.

Important Note :

Best Crete products are warranty against defective materials. Due to different substrate and working conditions, no guarantee of an application result or any liability claims. The users are required to have a test ahead based on their intended use.

BEST CRETE (M) SDN BHD (969553-A) (GST/BCP NO: 001222787072),

NO.1, JALAN PERUSAHAAN 21/KS5, KAWASAN PERINDUSTRIAN KAMPUNG IDAMAN, 42000 PELABUHAN KLANG, SELANGOR DARUL EHSAN, MALAYSIA, TEL: +603-3167 1263, +603-3168 1263, +603-3162 5044 FAX: +603-3166 2263, EMAIL: marketing@bestcretepolymers.com.my WEBSITE: www.bestcretepolymers.com